

Typical Properties	Characteristics	Regulations
Color		Translucent
Dielectric Constant at 100 Hz		= 2.83
Dielectric Constant at 100 kHz		= 2.83
Dielectric Strength		= 500 volts per mil v/mil
Dissipation Factor at 100 Hz		< 0.001
Dissipation Factor at 100 kHz		= 0.001
Durometer - Shore A		= 45 Shore A
Elongation		= 660 %
Hydrophobic		
Linear CTE		= 370 um/m/Deg C
Nonflowable		
Room Temperature Cure - Hours		= 48 Hours
Shelf Life		= 360 Days
Specific Gravity @ 25C		= 1.1
Tack-Free Time-50% RH		= 55 Minutes
Temperature Range		-45 Deg C to 200 Deg C
Tensile Strength		= 940 psi
Volume Resistivity		= 4.4e+014 ohm-centimeters
Water Resistant		

*These values are typical properties and are not intended for use in preparing specifications.